



INSERT - 40 x 5 MILD STEEL FLAT BAR

Chemical Composition Limits Standard: AS2239* Zinc			Alloy: Z1
Element	Min	Max	
Cadmium	0.025	0.070	
Aluminium	0.10	0.50	
Silicon	—	0.005	
Copper	—	0.005	
Iron	—	0.005	
Lead	—	0.006	
Other Impurities	- Each	0.005	
	- Total	0.02	
Zinc		remainder	

* Corresponds to MIL-A-18001k alloy composition.

Notes

- Anodes are cast to comply with CAA's standard casting tolerances.
- All sharp edges removed for safe handling.
- Insert Steel - AS/NZS 3679.1 Grade 300 unless specified otherwise.

Rev	Details of Change(s)	Date	Drawn	Verified
1	Cathodic Diecasting Original	08 JUN 04	GPC	R.G.
2	2013 Catalogue Version (CAA Logo)	13 DEC 13	R.N.	R.G.

Nett Weight Kg (nominal)	Gross Weight Kg (nominal)
11.2	12.0



Cathodic Anodes Australasia

cathodicanodes.com.au

All dimensions are in mm (nominal)

Product Zinc Anode	
Part no. CDZ8-12-175S	Scale 1 : 2.5
Drawing No: CDQ-215	Rev Sheet 2 1 of 1
Drawn by: R Northey Date: 13 DEC 2013	
Mould No: 89 Strap Sample 04	

