


This drawing is the property of Cathodic Anodes Australasia. To be used with permission only.
 This drawing becomes an uncontrolled document once issued as hard or electronic copy.
 Customer to confirm current revision of drawing prior to ordering.



Chemical Composition Limits		Alloy:	
Element	min.	max.	A6
Standard: AS2239 (Most current revision)			
Aluminium			
Zinc	2.0	6.0	
Indium	0.01	0.02	
Cadmium	-	0.005	
Silicon	0.08	0.12	
Iron	-	0.12	
Magnesium	-	0.02	
Titanium	-	0.02	
Copper	-	0.006	
Tin	-	0.02	
Other Impurities			
- each	-	0.02	
- total	-	0.05	
Aluminium		remainder	

- Notes
- Anodes are cast to comply with CAA's standard casting tolerances
 - All sharp edges removed for safe handling
 - Anode Insert material to meet relevant Australian/International specifications

Rev	Details of Change(s)	Date	Drawn	Verified
1	Cathodic Diecasting Original	03 June 2009	B.L.	R.G.
2	2013 Catalogue Version (CAA Logo)	10 January 2014	R.N.	R.G.
3	Insert ID 17, 17.5 > 18	07 AUG 17	R.N.	R.G.

Nett Weight Kg (nominal)	Gross Weight Kg (nominal)	
0.700	N/A	
Date	Drawn	Verified



Product Aluminium Anode	
Part no. CDA-Type C (A6)	Scale 1 : 1
Drawing No: CD1213	Rev Sheet 3 1 of 1
Drawn by: R Northey Date: 07 AUG 2017	
Mould No: 82	

All dimensions are in mm (nominal)