


This drawing is the property of Cathodic Anodes Australasia. To be used with permission only.
 This drawing becomes an uncontrolled document once issued as hard or electronic copy.
 Customer to confirm current revision of drawing prior to ordering.


Component View - Scale 1 : 6.75




1686 O/L

3.4 Ø Mild Steel (Wire) Core - Welded at Cap End

3/4 BSPT (Mild Steel) Cap



21 Ø



27 Hex

21 mm Ø Low Potential (AS2239-M2) Magnesium Rod

Chemical Composition Limits			Alloy:
Standard: AS2239 (Most current revision)			M2
Magnesium, Low Potential			
Element	min.	max.	
Aluminium	2.5	3.5	
Zinc	0.7	1.3	
Manganese	0.20	1.5	
Silicon	-	0.05	
Copper	-	0.006	
Iron	-	0.003	
Nickel	-	0.001	
Calcium	-	0.04	
Other Impurities			
- each	-	-	
- total	-	0.30	
Magnesium	remainder		

Notes

- Anodes are cast to comply with CAA's standard casting tolerances
- All sharp edges removed for safe handling
- Anode insert material to meet relevant Australian/International specifications

		Nett Weight Kg (nominal)		Gross Weight Kg (nominal)	
		1.135		1.185	
Rev	Details of Change(s)	Drawn	Initials	Verified	Initials
1	2013 Catalogue Version	10 MAY 16	R.N.	10 MAY 16	R.G.



Cathodic Anodes Australasia

cathodicanodes.com.au

Product Magnesium Anode			
Part no. CDMR-M2-21-1686-A		Scale NTS	
Drawing No: CD2255		Rev 1	Sheet 1 of 1
Drawn by: R Northey Date: 10 MAY 2016			
All dimensions are in mm (nominal)			