


This drawing is the property of Cathodic Anodes Australasia. To be used with permission only.
 This drawing becomes an uncontrolled document once issued as hard or electronic copy.
 Customer to confirm current revision of drawing prior to ordering.



| Chemical Composition Limits | | | Alloy: |
|---|-----------|-------|-----------|
| Element | min. | max. | Z1 |
| Standard: AS2239* (Most current revision) | | | |
| Zinc | | | |
| Cadmium | 0.025 | 0.07 | |
| Aluminium | 0.10 | 0.50 | |
| Silicon | - | 0.005 | |
| Copper | - | 0.005 | |
| Iron | - | 0.005 | |
| Lead | - | 0.006 | |
| Other Impurities | | | |
| - each | - | 0.005 | |
| - total | - | 0.02 | |
| Zinc | remainder | | |

* Corresponds to MIL-DTL-18001L alloy composition

Notes

1. Anodes are cast to comply with CAA's standard casting tolerances
2. All sharp edges removed for safe handling
3. Anode insert material to meet relevant Australian/International specifications

All dimensions are in mm (nominal)

| Rev | Details of Change(s) | Date | Drawn | Verified |
|-----|-----------------------------------|----------------|-------|----------|
| 1 | 2013 Catalogue Version (CAA Logo) | 25 August 2016 | R.N. | R.G. |
| | | | | |
| | | | | |
| | | | | |

| Nett Weight | Gross Weight |
|--------------|--------------|
| Kg (nominal) | Kg (nominal) |
| 0.270 | 0.270 |



Cathodic Anodes Australasia

cathodicanodes.com.au

| | | | |
|---------------------|-------------------|-------------------|---------------|
| Product | | Zinc Anode | |
| Part no. | CDZPN-63 U | Scale | 1 : 1 |
| Drawing No: | CD2311 | Rev | 1 |
| Drawn by: R Northey | Date: 25 AUG 2016 | Sheet | 1 of 1 |
| | | | |