




This drawing is the property of Cathodic Anodes Australasia. To be used with permission only. This drawing becomes an uncontrolled document once issued as hard or electronic copy. Customer to confirm current revision of drawing prior to ordering.



Chemical Composition Limits		Alloy:
Standard: AS2239* (Most current revision)		<b>Z1</b>
Zinc		
Element	min.	max.
Cadmium	0.025	0.07
Aluminium	0.10	0.50
Silicon	-	0.005
Copper	-	0.005
Iron	-	0.005
Lead	-	0.006
Other Impurities		
- each	-	0.005
- total	-	0.02
Zinc	remainder	

\* Corresponds to MIL-DTL-18001L alloy composition

- Notes
- Anodes are cast to comply with CAA's standard casting tolerances
  - All sharp edges removed for safe handling
  - Anode insert material to meet relevant Australian/International specifications

Nett Weight Kg (nominal)	Gross Weight Kg (nominal)
<b>2.05</b>	<b>2.30</b>

Rev	Details of Change(s)	Date	Initials
1	For manufacture	23JUL09	B
2	CAA Logo	08 Feb 22	B.G.

**CAA**  
Cathodic Anodes Australasia  
cathodicanodes.com.au

Product <b>Zinc Anode</b>		Scale <b>1 to 2</b>	
Part no. <b>CDZ3-7S 2.2kg LS</b>		Rev	Sheet
Drawing no. <b>CD1245</b>		<b>2</b>	<b>1 of 1</b>
Drawn by: BL		Date: 23JUL09	



All dimensions are in mm (nominal)