


This drawing is the property of Cathodic Anodes Australasia. To be used with permission only. This drawing becomes an uncontrolled document once issued as hard or electronic copy. Customer to confirm current revision of drawing prior to ordering.



Chemical Composition Limits			Alloy: A6
Element	min.	max.	
Standard: AS2239 (Most current revision)			
Aluminium			
Zinc	2.0	6.0	
Indium	0.01	0.02	
Cadmium	-	0.005	
Silicon	0.08	0.12	
Iron	-	0.12	
Magnesium	-	0.02	
Titanium	-	0.02	
Copper	-	0.006	
Tin	-	0.02	
Other Impurities	-	-	
- each	-	0.02	
- total	-	0.05	
Aluminium	remainder		

- Notes
- Anodes are cast to comply with CAA's standard casting tolerances
 - All sharp edges removed for safe handling
 - Anode insert material to meet relevant Australian/International specifications



Nett Weight Kg (nominal)	Gross Weight Kg (nominal)	
10.0	11.3	
Date	Drawn	Verified
30 MAR 2017	R.N.	J.L.
Rev	Details of Change(s)	
1	For Quotation	



Product		
Aluminium Anode		
Part no.	Scale	
CDA-11S Type 1 (A6) Special	1 : 4	
Drawing No: CD2368	Rev	Sheet
	1	1 of 1
Drawn by: R Northey	Date: 30 MAR 2017	
Mould No: 8	Strap Sample: 26 (Mod)	

All dimensions are in mm (nominal)