


This drawing is the property of Cathodic Anodes Australasia. To be used with permission only. This drawing becomes an uncontrolled document once issued as hard or electronic copy. Customer to confirm current revision of drawing prior to ordering.



| Chemical Composition Limits | | Alloy: |
|-------------------------------------------|-----------|-----------|
| Standard: AS2239* (Most current revision) | | Z1 |
| Zinc | | |
| Element | min. | max. |
| Cadmium | 0.025 | 0.07 |
| Aluminium | 0.10 | 0.50 |
| Silicon | - | 0.005 |
| Copper | - | 0.005 |
| Iron | - | 0.005 |
| Lead | - | 0.006 |
| Other Impurities | | |
| - each | - | 0.005 |
| - total | - | 0.02 |
| Zinc | remainder | |

* Corresponds to MIL-DTL-18001L alloy composition

- Notes
- Anodes are cast to comply with CAA's standard casting tolerances
 - All sharp edges removed for safe handling
 - Anode insert material to meet relevant Australian/International specifications



| Rev | Details of Change(s) | Date | Drawn | Verified |
|-----|---------------------------|-----------------|-------|----------|
| 1 | For Quotation | 31 October 2017 | R.N. | J.L. |
| 2 | "CDZ" Part Number Created | 19 April 2018 | R.N. | J.L. |

| Nett Weight Kg (nominal) | Gross Weight Kg (nominal) |
|-----------------------------|------------------------------|
| 2.95 | 3.10 |

CAA
Cathodic Anodes Australasia
cathodicanodes.com.au

| | | | |
|---------------------------------------|-------------------|------------------------------------|------------------------|
| Product Zinc Anode | | All dimensions are in mm (nominal) | |
| Part no. CDZ8-16-2.0-1H | QuickSilver Anode | Scale 1 : 2 | |
| Drawing No: CD2406 | | Rev 1 | Sheet 1 of 1 |
| Drawn by: R Northey Date: 31 OCT 2017 | | | |
| Mould No: Custom | Tooling: Custom | | |