



This drawing is the property of Cathodic Anodes Australasia. To be used with permission only. This drawing becomes an uncontrolled document once issued as hard or electronic copy. Customer to confirm current revision of drawing prior to ordering.

Component View - Scale 1 : 5



Chemical Composition Limits			Alloy: <b>M1C</b>
Element	min.	max.	
Aluminium	-	0.01	
Zinc	-	0.02	
Manganese	0.50	1.3*	
Silicon	-	0.05	
Copper	-	0.02	
Iron	-	0.03	
Nickel	-	0.001	
Calcium	-	0.04	
Other Impurities			
- each	-	0.05	
- total	-	0.30	
Magnesium	remainder		

Notes

1. Anodes are cast to comply with CAA's standard casting tolerances
2. All sharp edges removed for safe handling
3. Anode insert material to meet relevant Australian/International specifications

Nett Weight Kg (nominal)		Gross Weight Kg (nominal)			
<b>0.800</b>		<b>0.850</b>			
Rev	Details of Change(s)	Drawn	Initials	Verified	Initials
1	2013 Catalogue Version	01 NOV 17	R.N.	01 NOV 17	R.G.



cathodicanodes.com.au

Product <b>Magnesium Anode</b>	
Part no. <b>CDMR-M1-21-1190-A</b>	Scale <b>NTS</b>
Drawing No: <b>CD2409</b>	Rev 1 Sheet 1 of 1
Drawn by: R Northey Date: 01 NOV 2017	
All dimensions are in mm (nominal)	