


This drawing is the property of Cathodic Anodes Australasia. To be used with permission only.
 This drawing becomes an uncontrolled document once issued as hard or electronic copy.
 Customer to confirm current revision of drawing prior to ordering.



INSERT - 40 x 5 MILD STEEL FLAT BAR

C D Q
 CAST INDENTATION LETTERING

All dimensions are in mm (nominal)

Chemical Composition Limits			Alloy: A2
Standard: AS2239 (Most current revision)			
Aluminium			
Element	min.	max.	
Zinc	3.0	5.0	
Indium	0.02	0.05	
Cadmium	-	0.005	
Silicon	-	0.20	
Iron	-	0.12	
Magnesium	0.6	2.2	
Titanium	0.02	0.05	
Copper	-	0.006	
Other Impurities			
- each	-	0.02	
- total	-	0.05	
Aluminium	remainder		

Notes

- Anodes are cast to comply with CAA's standard casting tolerances
- All sharp edges removed for safe handling
- Anode insert material to meet relevant Australian/International specifications



Rev	Details of Change(s)	Nett Weight		Gross Weight		
		Kg (nominal)		Kg (nominal)		
Date	Drawn	Verified				
1	2013 Catalogue Version	17 JAN 2018	R.N.	J.L.		

CAA
 Cathodic Anodes Australasia
cathodicanodes.com.au

Product Aluminium Anode		Scale 1 : 4	
Part no. CDA-15S Type 1 (A2)		Rev 1	Sheet 1 of 1
Drawing No: CD2430			
Drawn by: R Northey Date: 17 JAN 2018			
Mould No: 8	Strap Sample: 08		