


This drawing is the property of Cathodic Anodes Australasia. To be used with permission only.  
 This drawing becomes an uncontrolled document once issued as hard or electronic copy.  
 Customer to confirm current revision of drawing prior to ordering.



C D Q  
 CAST INDENTATION LETTERING

Chemical Composition Limits		Alloy:
Standard: AS2239 (Most current revision)		A1
Aluminium		
Element	min.	max.
Zinc	2.1	2.7
Indium	0.017	0.025
Cadmium	0.008	0.012
Silicon	-	0.20
Iron	-	0.12
Copper	-	0.006
Other Impurities	-	-
- each	-	0.02
- total	-	0.05
Aluminium	remainder	

- Notes
1. Anodes are cast to comply with CAA's standard casting tolerances
  2. All sharp edges removed for safe handling
  3. Anode insert material to meet relevant Australian/International specifications



Nett Weight Kg (nominal)	Gross Weight Kg (nominal)
<b>7.60</b>	<b>8.80</b>

**CAA**  
 Cathodic Anodes Australasia  
 cathodicanodes.com.au

Product		Aluminium Anode	
Part no.	CDA-9S Type 3 (A1)	Scale	1 : 4
Drawing No:	CD3136	Rev	2
Sheet	1 of 1		
Drawn by:	R Northey	Date:	17 DEC 2013
Mould No:	11	Strap Sample:	01

Rev	Details of Change(s)	Date	Drawn	Verified
1	Cathodic Diecasting Original	31 OCT 2008	B.L.	R.G.
2	2013 Catalogue Version (CAA Logo)	17 DEC 2013	R.N.	R.G.

All dimensions are in mm (nominal)