


This drawing is the property of Cathodic Anodes Australasia. To be used with permission only.
 This drawing becomes an uncontrolled document once issued as hard or electronic copy.
 Customer to confirm current revision of drawing prior to ordering.



C D Q
 CAST INDENTATION LETTERING

Chemical Composition Limits			Alloy: A1
Standard: AS2239 (Most current revision)			
Aluminium			
Element	min.	max.	
Zinc	2.1	2.7	
Indium	0.017	0.025	
Cadmium	0.008	0.012	
Silicon	-	0.20	
Iron	-	0.12	
Copper	-	0.006	
Other Impurities			
- each	-	0.02	
- total	-	0.05	
Aluminium	remainder		

- Notes
1. Anodes are cast to comply with CAA's standard casting tolerances
 2. All sharp edges removed for safe handling
 3. Anode insert material to meet relevant Australian/International specifications



Rev		Details of Change(s)	Date	Drawn	Verified
1		Cathodic Diecasting Original	13 APR 2010	B.L.	R.G.
2		2013 Catalogue Version (CAA Logo)	17 DEC 2013	R.N.	R.G.

Nett Weight
Kg (nominal)
10.5

Gross Weight
Kg (nominal)
11.7

Cathodic Anodes Australasia

cathodicanodes.com.au

Product Aluminium Anode		Scale 1 : 4	
Part no. CDA-12S (A1)		Rev 2	Sheet 1 of 1
Drawing No: CD3138		Mould No: 11	
Drawn by: R Northey		Date: 17 DEC 2013	
Mould No: 11		Strap Sample: 01	

All dimensions are in mm (nominal)