




This drawing is the property of Cathodic Anodes Australasia. To be used with permission only.
 This drawing becomes an uncontrolled document once issued as hard or electronic copy.
 Customer to confirm current revision of drawing prior to ordering.



| Chemical Composition Limits | | | Alloy: Z1 |
|---|-----------|-------|---------------------|
| Standard: AS2239* (Most current revision) | | | |
| Zinc | | | |
| Element | min. | max. | |
| Cadmium | 0.025 | 0.07 | |
| Aluminium | 0.10 | 0.50 | |
| Silicon | - | 0.005 | |
| Copper | - | 0.005 | |
| Iron | - | 0.005 | |
| Lead | - | 0.006 | |
| Other Impurities | | | |
| - each | - | 0.005 | |
| - total | - | 0.02 | |
| Zinc | remainder | | |

* Corresponds to MIL-DTL-18001L alloy composition

- Notes
- Anodes are cast to comply with CAA's standard casting tolerances
 - All sharp edges removed for safe handling
 - Anode insert material to meet relevant Australian/International specifications



| Nett Weight Kg (nominal) | Gross Weight Kg (nominal) |
|-----------------------------|------------------------------|
| 2.00 | 2.00 |

| Rev | Details of Change(s) | Date | Drawn | Verified |
|-----|------------------------------|-----------|-------|----------|
| 1 | Cathodic Diecasting Original | 25 FEB 09 | B.L. | R.G. |
| 2 | 2013 Catalogue Version | 20 DEC 13 | R.N. | R.G. |
| | | | | |
| | | | | |

CAA
Cathodic Anodes Australasia
cathodicanodes.com.au

| | | | |
|-------------------------------|--|-----------------------|------------------------|
| Product Zinc Anode | | Scale 1 : 1 | |
| Part no. CDZ2-64-75 | | Rev 2 | Sheet 1 of 1 |
| Drawing No: CD3710 | | Date: 20 DEC 2013 | |
| Drawn by: R Northey | | Mould No: 62 | |

All dimensions are in mm (nominal)

