




This drawing is the property of Cathodic Anodes Australasia. To be used with permission only.
 This drawing becomes an uncontrolled document once issued as hard or electronic copy.
 Customer to confirm current revision of drawing prior to ordering.



Chemical Composition Limits			Alloy:
Standard: AS2239* (Most current revision)			Z1
Zinc			
Element	min.	max.	
Cadmium	0.025	0.07	
Aluminium	0.10	0.50	
Silicon	-	0.005	
Copper	-	0.005	
Iron	-	0.005	
Lead	-	0.006	
Other Impurities			
- each	-	0.005	
- total	-	0.02	
Zinc		remainder	

* Corresponds to MIL-DTL-18001L alloy composition

- Notes
1. Anodes are cast to comply with CAA's standard casting tolerances
 2. All sharp edges removed for safe handling
 3. Anode insert material to meet relevant Australian/International specifications



All dimensions are in mm (nominal)

Rev	Details of Change(s)	Date	Nett Weight		Gross Weight	
			Kg (nominal)		Kg (nominal)	
			1.70	N/A		
1	Cathodic Diecasting Original	N/A				
2	2013 Catalogue Version (CAA Logo)	17 January 2014		<i>R.N.</i>	<i>R.G.</i>	

CAA
Cathodic Anodes Australasia

cathodicanodes.com.au

Product		Zinc Anode	
Part no.		CDZ3-7 1.7 kg	
Drawing No: CD3717		Rev	Sheet
		2	1 of 1
Drawn by: R Northey Date: 17 JAN 2014			
Mould No: 73			

