


This drawing is the property of Cathodic Anodes Australasia. To be used with permission only. This drawing becomes an uncontrolled document once issued as hard or electronic copy. Customer to confirm current revision of drawing prior to ordering.



Chemical Composition Limits		Alloy:
Standard: AS2239 (Most current revision)		A6
Aluminium		
Element	min.	max.
Zinc	2.0	6.0
Indium	0.01	0.02
Cadmium	-	0.005
Silicon	0.08	0.12
Iron	-	0.12
Magnesium	-	0.02
Titanium	-	0.02
Copper	-	0.006
Tin	-	0.02
Other Impurities	-	-
- each	-	0.02
- total	-	0.05
Aluminium	remainder	

- Notes
1. Anodes are cast to comply with CAA's standard casting tolerances
 2. All sharp edges removed for safe handling
 3. Anode insert material to meet relevant Australian/International specifications



Nett Weight Kg (nominal)	Gross Weight Kg (nominal)	Date	Drawn	Verified
9.0	10.2	22 JUN 15	R.N.	J.L.
Rev	Details of Change(s)			
1	For Manufacture			



Cathodic Anodes Australasia

cathodicanodes.com.au

Product		Aluminium Anode	
Part no.	CDA-10S Type 2 (A6)		Scale
Drawing No: CD3974		Rev	Sheet
		1	1 of 1
Drawn by: R Northey	Date: 22 JUN 2015		
Mould No: 10	Strap Sample 08		

All dimensions are in mm (nominal)